

REMARKS


Claims in the case are 1 to 16. Claims 2-16 have been amended herein.

Claims 2-16 of the above-identified patent application have been amended as to form, for example, replacing "characterized in that" with --wherein--, and converting multi-dependent claims to dependent claims. Claim 16 has been changed from a use claim to a method claim by amendment herein. The title has been changed to correspond to the related International Patent Publication No. WO 00/23506. The patent application has also been amended to include an abstract on a separate page, which is included herewith. The amendments presented herein do not represent the entry of new matter into the application. Applicants respectfully request entry of this amendment.

Respectfully submitted,

HOLGER EGGERS
ANDREAS GASSE
GREGOR KASCHEL
RAINER BRANDT
BERND EILERS

By



James R. Franks
Agent for Applicants
Reg. No. 42,552

Bayer Corporation
100 Bayer Road
Pittsburgh, Pennsylvania 15205-9741
(412) 777-8339
FACSIMILE PHONE NUMBER:
(412) 777-5449
s:\kgb\jrf036pa

VERSIONS WITH MARKINGS TO SHOW CHANGES MADE

IN THE SPECIFICATION: (Marked-Up)

The following is a version of the title at the top of page 1, with markings to show changes made thereto in the present Preliminary Amendment.

[Transparent high-strength polyamide film]

TRANSPARENT HIGH STRENGTH POLYAMIDE FILM

IN THE CLAIMS: (Marked-Up)

The following are versions of the amended claims with markings to show changes made thereto in the present Preliminary Amendment.

2. (Once Amended, Marked-Up) The [F]film [according to] of [c]Claim 1, characterised in that] wherein layer (I) contains, in addition to polyamide 6, a polyamide selected from the group consisting of polyamide 6, polyamide 10, polyamide 12, polyamide 66, polyamide 610, polyamide 6I, polyamide 612, polyamide 6/66, polyamide 6I/6T, polyamide MXD6, polyamide 6/6I, polyamide 6/6T, polyamide 6/IPDI, copolymers of the monomers forming those polymers, or mixtures of those polymers or copolymers.

3. (Once Amended, Marked-Up) The [F]film [according to either] of [c]Claim 1 [or claim 2, characterised in that] wherein the particles dispersed in layer (I) have particles that, in two directions that are perpendicular to each other and are randomly selectable for each particle, each have a dimension of at least ten times the dimension of the particles in the direction having the smallest dimension.

4. (Once Amended, Marked-Up) The [F]film [according to any one] of [c]Claim[s] 1 [to 3, characterised in that] wherein the particles used in layer (I) are layered silicates.

5. (Once Amended, Marked-Up) The [Multi-layer] film [according to any one] of [c]Claim[s] 1 [to 4, characterised in that it] wherein said film contains, in addition to one or more layers (I), further polyamide-containing layers (II) containing no or less than 10 ppm nano-scale nucleating agent.

6. (Once Amended, Marked-Up) The [F]film [according to any one] of [c]Claim[s] 1 [to 5, characterised in that it] wherein said film contains one or more EVOH-containing layers (III).

7. (Once Amended, Marked-Up) The [Multi-layer] film [according to any one] of [c]Claim[s] 1 [to 6, characterised in that it] wherein said film has an at least single-layer sealing layer (V) on one outer side of the multi-layer film.

8. (Once Amended, Marked-Up) The [Multi-layer] film [according to any one] of [c]Claim[s] 1 [to 7, characterised in that it] wherein said film contains one or more adhesion-promoting layers (IV).

9. (Once Amended, Marked-Up) The [Multi-layer] film [according to any one] of [c]Claim[s] 1 [to 8, characterised in that it] wherein said film contains, in addition to the layers (I) and optionally (II), (III), (IV) and/or (V), one or more further polymeric layers.

10. (Once Amended, Marked-Up) The [F]film [according to any one of claims] of Claim 1 [to 5, characterised in that it] wherein said film has only polyamide-containing layers.

11. (Once Amended, Marked-Up) The [F]film [according to any one of claims] of Claim 1 [to 6, characterised in that it] wherein said film has only polyamide-containing and EVOH-containing layers.

12. (Once Amended, Marked-Up) The [F]film [according to either claim] of Claim 10 [or claim 11, characterised in that it] wherein said film has a thickness of from 13 to 30 μm .

13. (Once Amended, Marked-Up) The [F]film [according to any one of claims] of Claim 1 [to 12, characterised in that it] wherein said film has been produced in the form of a flat film.

14. (Once Amended, Marked-Up) The [F]film [according to any one of claims] of Claim 1 [to 13, characterised in that] wherein layer (I) forms an outer layer of the film.

15. (Once Amended, Marked-Up) The [F]film [according to any one of claims] of Claim 1 [to 14, characterised in that] wherein at least one layer (I) is subjected, after extrusion, to a stretching operation selected from: stretching only in the longitudinal direction[.]; stretching only in the transverse direction[.]; stretching first in the longitudinal and then in the transverse direction[.]; stretching in the longitudinal and transverse directions simultaneously[.]; [or] and combinations thereof.

16. (Once Amended, Marked-Up) [Use of a multi-layer film according to any one of claims] A method of using the film of Claim 1 [to 15] in the packaging of foodstuffs on shape-fill-seal machines.